



TEST LAB

1220 TAMARA LANE
WARSAW, MO 65355
660-438-8998

PART DESCRIPTION AND SIZE(LXWXH): Stainless tube, 5" Wide, 7" Tall

FINISH DESIRED: Deburr and Polish

MEDIA USED: Step 1: AC3S50A ceramic, Step 2: Walnut shell with chromium oxide.

TIME PROCESSED: Step 1: One hour, Step 2: 8 hours.

MACHINE USED: Burr King VibraKing 45



AC3S50A 5/8 x 1/4"



WALNUT SHELL WITH
CHROMIUM OXIDE



BEFORE



AFTER